

هيئة التقييس لدول مجلس التعاون لدول الخليج العربية

G.C.C STANDARDIZATION ORGANIZATION FOR (GSO)

GSO 01/DS/ ISO 14527-3:2016

ISO 14527-3:1999

البلاستيك - المركبات المقولبة لبودرة اليوريا - فورمالدهيد و اليوريا /

ميلامين فورمالدهيد (UF-and UF/MF-PMCs) -

الجزء 3 :

المتطلبات لمركبات مقولبة مختارة

Plastics – urea-formaldehyde and urea/melamine – formaldehyde
powder moulding compounds (UF-and UF/MF-PMCs)-

Part 3 :

Requirements for selected moulding compounds

Prepared by

GSO / TC 1 of Chemistry and Textile standards

ICS 83.080.10

This document is a Draft Gulf Standard circulated for comment. It is therefore subjected to change and may not be referred as Gulf standard until approved by the board of directors.

تقديم

هيئة التقييس لدول مجلس التعاون لدول الخليج العربية هيئة إقليمية تضم في عضويتها الأجهزة الوطنية للمواصفات والمقاييس في دول الخليج العربية ، ومن مهام الهيئة إعداد المواصفات القياسية الخليجية بواسطة لجان فنية متخصصة .

وقد قامت هيئة التقييس لدول مجلس التعاون لدول الخليج العربية ضمن برنامج عمل اللجنة الفنية رقم(1) " اللجنة الفنية الخليجية للمواصفات الكيميائية والغزل والنسيج " بتبني المواصفة القياسية الدولية رقم ISO 14527-3:1999 "البلاستيك - المركبات المقولبة لبودرة اليوريا - فورمالدهيد و اليوريا / ميلامين فورمالدهيد (UF-and UF/MF-PMCs)- الجزء 3 :المتطلبات لمركبات مقولبة مختارة " ، و التي أصدرتها " المنظمة الدولية للتقييس " و تمت ترجمتها إلى اللغة العربية .

و قامت (دولة قطر) بإعداد مشروع هذه المواصفة.

وقد اعتمدت هذه المواصفة كمواصفة قياسية خليجية دون إدخال أية تعديلات فنية عليها في اجتماع مجلس إدارة الهيئة رقم () ، الذي عقد بتاريخ / / هـ ، الموافق / /

Foreword

Standardization Organization for GCC (GSO) is a regional Organization which consists of the National Standards Bodies of GCC member States. One of GSO main functions is to issue Gulf Standards /Technical regulation through specialized technical committees (TCs).

GSO through the technical program of committee TC 1 " Gulf technical committee for Chemical and textile standards " adopt International standard ISO 14527-3:1999 "Plastics – urea-formalhyde and urea/melamine – formaldehyde powder moulding compounds (UF-and UF/MF-PMCs)–Part 3 :Requirements for selected moulding compounds " , issued by (*International Organization for Standardization*), which has been translated into Arabic . The Draft Standard has been prepared by (state of Qatar). This standard has been approved as Gulf Standard without any technical modifications by GSO Board of Directors in its meeting No..../....held on / / H , / / G

**Plastics — Urea-formaldehyde and
urea/melamine-formaldehyde powder
moulding compounds (UF- and
UF/MF-PMCs) —**

**Part 3:
Requirements for selected moulding
compounds**

*Plastiques — Poudres à mouler à base d'urée-formaldéhyde et
d'urée/mélanine-formaldéhyde (UF- et UF/MF-PMC) —*

Partie 3: Exigences relatives à certaines poudres à mouler



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 14527 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 14527-3 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 12, *Thermosetting materials*.

After a transition period of, at the most, four years, the three parts of ISO 14527 (see below), together with the three parts of ISO 14528, will replace ISO 2112:1990, of which they constitute a technical revision.

ISO 14527 consists of the following parts, under the general title *Plastics — Urea-formaldehyde and urea/melamine-formaldehyde powder moulding compounds (UF- and UF/MF-PMCs)*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*
- *Part 3: Requirements for selected moulding compounds*

Annex A of this part of ISO 14527 is for information only.

Plastics — Urea-formaldehyde and urea/melamine-formaldehyde powder moulding compounds (UF- and UF/MF-PMCs) —

Part 3: Requirements for selected moulding compounds

1 Scope

This part of ISO 14527 specifies the requirements for the physical and chemical properties of urea-formaldehyde and urea/melamine-formaldehyde powder moulding compounds (UF- and UF/MF-PMCs) and compression- or injection-moulded test specimens produced from them.

It is limited to those powder moulding compounds whose composition and properties are significantly different. It is further limited to those moulding compounds which are of general technical and/or economic importance.

The properties which are used to characterize the moulding compounds, the test methods and the test conditions are selected from those given in ISO 14527-2.

The moulding compounds are divided into types according to their composition and properties. The various types are designated using the designation system defined in ISO 14527-1.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 14527. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 14527 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 472:1999, *Plastics — Vocabulary*.

ISO 2112:1990, *Plastics — Urea-formaldehyde moulding materials — Specification*.

ISO 14527-1:1999, *Plastics — Urea-formaldehyde and urea/melamine-formaldehyde powder moulding compounds (UF- and UF/MF-PMCs) — Part 1: Designation system and basis for specifications*.

ISO 14527-2:1999, *Plastics — Urea-formaldehyde and urea/melamine-formaldehyde powder moulding compounds (UF- and UF/MF-PMCs) — Part 2: Preparation of test specimens and determination of properties*.

3 Terms and definitions

For the purposes of this part of ISO 14527, the terms and definitions given in ISO 472, ISO 14527-1 and ISO 14527-2 apply.

4 Requirements

4.1 Property values

In order for a urea-formaldehyde or urea/melamine-formaldehyde powder moulding compound to be considered as complying with this part of ISO 14527, it shall meet the requirements given in Table 1.

Table 1 gives the mean value obtained for the set of test specimens used to determine a particular property. Individual values of properties 2.1, 2.2, 2.3 and 2.4 shall be within 10 % of the mean value, and individual values of properties 3.1 and 3.2 shall be within 5 °C of the mean value.

No specific limits are placed on rheological and processing properties. However, suitable rheological and processing properties are essential for the satisfactory use of a moulding compound. The test methods and test conditions used shall be as agreed between the interested parties.

In addition, for some applications, it may be useful for information to be made available on other properties, for example:

- cure time;
- particle size;
- moisture content.

If this is so, these properties and test methods, as well as the test conditions to be used, shall be as agreed between the interested parties.

4.2 Filler/reinforcement type and content

In order for a phenolic powder moulding compound to be considered as complying with this part of ISO 14527, the nature, form and content by mass of its filler/reinforcement shall be as given in the designation of the moulding compound (see ISO 14527-1:1999, subclause 4.2).

Table 1 — Property requirements for UF- and UF/MF-PMCs containing (LD+MD), (WD+MD) or (LD+S) as filler

					1	2	3	4
					Type: PMC ISO 14527-...			
Property	Unit	Processing ^a	Max. or min.	UF (LD10+MD30),X,E to (LD20+MD20),X,E	UF (LD10+MD30) to (LD20+MD20)	UF (WD30+MD20) to (WD40+MD10)	UF/MF (LF20+S10) to (LF30+S20)	
1	Rheological and processing properties							
1.1	To be agreed between the interested parties							
2	Mechanical properties							
2.1	Stress at break, σ_B	MPa	Q M	\geq \geq	45 55	45 55	35 40	^b —
2.2	Flexural strength, σ_{fM}	MPa	Q M	\geq \geq	80 100	80 1000	70 80	80 —
2.3	Charpy impact strength, a_{cU}	kJ/m ²	Q M	\geq \geq	5,0 7,5	5,0 7,5	4,5 5,0	6,5 —
2.4	Charpy notched impact strength, a_{cA}	kJ/m ²	Q M	\geq \geq	1,1 1,3	1,1 1,3	1,0 1,0	1,5 —
3	Thermal properties							
3.1	Temperature of deflection under load, $T_f1,8$	°C	Q/M	\geq	130	130	130	130
3.2	Temperature of deflection under load, $T_f8,0$	°C	Q/M	\geq	90	90	90	80
3.3	Flammability (glow bar), BH	—	Q/M	\leq	BH 2-10	BH 2-10	BH 2-10	^b
4	Electrical properties							
4.1	Dissipation factor, $\tan \delta 100$	—	Q/M	\leq	0,1	—	—	—
4.2	Volume resistivity, ρ_e	$\Omega \cdot \text{cm}$	Q/M	\geq	10^{12}	—	—	10^{10}
4.3	Surface resistivity, σ_e	Ω	Q/M	\geq	10^{11}	10^{11}	10^{11}	10^{10}
4.4	Proof tracking index, PTI	—	Q/M	\geq	600	600	600	500
5	Other properties							
5.1	Water absorption, W_w24	mg	Q/M	\leq	150	150	200	100
5.2		% by mass		\leq	—	—	—	—
^a Q = Compression moulding M = Injection moulding ^b Limit will be inserted when agreed on within TC61/SC12.								
NOTE 1 See ISO 14527-2:1999, Tables 3 and 4, columns 3, 4, and 7, for the methods to be used for the preparation of test specimens and the determination of properties.								
NOTE 2 In view of the differences between the property-value limits for compression-moulding and injection-moulding materials, the likely variations in test results and the wide range of properties covered, it should not be assumed that materials having the same designation are exactly equivalent.								

Annex A (informative)

Comparison of designations

Table A.1 — Comparison of designations used for UF- and UF/MF-PMCs in national and international standards

National or international standard	1	2	3	4
	Type: PMC ISO 14527-. . .			
ISO 14527-3:1999	UF (LD10+MD30),X,E to (LD20+MD20),X,E	UF (LD10+MD30) to (LD20+MD20)	UF (WD30+MD20) to (WD40+MD10)	UF/MF (LF20+S10) to (LF30+S20)
ISO 2112:1990	UF A10	UF A11	UF A20	—
ASTM D 705-81	—	—	—	—
BS 1322:1992	UF A10	UF A11	UF A20	—
DIN 7708-3:1975	131.5	131	(130) ^a	—
JIS K 6916:1995	UM-E	UM-G	—	—
NF	—	—	—	—
^a Former DIN type (not included in DIN 7708-3:1975).				

